



5/19/2011

PRODUCT RELIABILITY REPORT
FOR

DS3640, Rev A6

Maxim Integrated Products

**4401 South Beltwood Parkway
Dallas, TX 75244-3292**

Prepared by:

**Don Lipps
Manager, Reliability Engineering
Maxim Integrated Products
4401 South Beltwood Pkwy.
Dallas, TX 75244-3292
Email: don.lipps@maxim-ic.com
ph: 972-371-3739**

Conclusion:

The following qualification successfully meets the quality and reliability standards required of all Maxim products:

DS3640, Rev A6

In addition, Maxim's continuous reliability monitor program ensures that all outgoing product will continue to meet Maxim's quality and reliability standards. The current status of the reliability monitor program can be viewed at <http://www.maxim-ic.com/TechSupport/dsreliability.html>.

Device Description:

A description of this device can be found in the product data sheet. You can find the product data sheet at http://dbserv.maxim-ic.com/l_datasheet3.cfm.

Reliability Derating:

The Arrhenius model will be used to determine the acceleration factor for failure mechanisms that are temperature accelerated.

$AfT = \exp((Ea/k)(1/T_u - 1/T_s)) = tu/ts$
AfT = Acceleration factor due to Temperature
tu = Time at use temperature (e.g. 55°C)
ts = Time at stress temperature (e.g. 125°C)
k = Boltzmann's Constant (8.617×10^{-5} eV/K)
Tu = Temperature at Use (°K)
Ts = Temperature at Stress (°K)
Ea = Activation Energy (e.g. 0.7 ev)

The activation energy of the failure mechanism is derived from either internal studies or industry accepted standards, or activation energy of 0.7ev will be used whenever actual failure mechanisms or their activation energies are unknown. All deratings will be done from the stress ambient temperature to the use ambient temperature.

An exponential model will be used to determine the acceleration factor for failure mechanisms, which are voltage accelerated.

$AfV = \exp(B(V_s - V_u))$
AfV = Acceleration factor due to Voltage
Vs = Stress Voltage (e.g. 7.0 volts)
Vu = Maximum Operating Voltage (e.g. 5.5 volts)
B = Constant related to failure mechanism type (e.g. 1.0, 2.4, 2.7, etc.)

The Constant, B, related to the failure mechanism is derived from either internal studies or industry accepted standards, or a B of 1.0 will be used whenever actual failure mechanisms or their B are unknown. All deratings will be done from the stress voltage to the maximum operating voltage. Failure rate data from the operating life test is reported using a Chi-Squared statistical model at the 60% or 90% confidence level (Cf).

The failure rate, Fr, is related to the acceleration during life test by:

$Fr = X/(ts * AfV * AfT * N * 2)$
X = Chi-Sq statistical upper limit
N = Life test sample size

Failure Rates are reported in FITs (Failures in Time) or MTTF (Mean Time To Failure). The FIT rate is related to MTTF by:

$$\text{MTTF} = 1/\text{Fr}$$

NOTE: MTTF is frequently used interchangeably with MTBF.

The calculated failure rate for this device/process is:

FAILURE RATE:	MTTF (YRS):	163796	FITS:	0.7
DEVICE HOURS:		1314743138	FAILS:	0

Only data from Operating Life or similar stresses are used for this calculation.

The parameters used to calculate this failure rate are as follows:

Cf: 60%	Ea: 0.7	B: 0	Tu: 25 °C	Vu: 3.6 Volts
----------------	----------------	-------------	------------------	----------------------

The reliability data follows. At the start of this data is the device information. The next section is the detailed reliability data for each stress. The reliability data section includes the latest data available and may contain some generic data. **Bold** Product Number denotes specific product data.

Device Information:

Process: SA E35X-0.5um, 5V CMOS with embedded Array EEPROM, embedded RSE EEPROM, 18V CMOS, VNPN, P2-P1 Cap, LVMOSCAP, HVMOSCAP, Varactor Cap, CrSi R's & Laser Fuses, 3LM.
 Passivation: TEOS Oxide-Nitride Passivation
 Die Size: 150 x 130
 Number of Transistors: 258322
 Interconnect: Aluminum / 0.5% Copper
 Gate Oxide Thickness: 120 Å

ESD HBM

DESCRIPTION	DATE CODE/PRODUCT/LOT	CONDITION	READPOIN	QTY	FAILS	FA#
ESD SENSITIVITY	1108 DS3640	ZX148848AA JESD22-A114 HBM 500 VOLTS	1	PUL'S	5	0
ESD SENSITIVITY	1108 DS3640	ZX148848AA JESD22-A114 HBM 1000 VOLTS	1	PUL'S	5	0
ESD SENSITIVITY	1108 DS3640	ZX148848AA JESD22-A114 HBM 1500 VOLTS	1	PUL'S	5	0
ESD SENSITIVITY	1108 DS3640	ZX148848AA JESD22-A114 HBM 2000 VOLTS	1	PUL'S	5	0
ESD SENSITIVITY	1108 DS3640	ZX148848AA JESD22-A114 HBM 2500 VOLTS	1	PUL'S	5	0
Total:						0

LATCH-UP

DESCRIPTION	DATE CODE/PRODUCT/LOT	CONDITION	READPOIN	QTY	FAILS	FA#
LATCH-UP I	1108 DS3640	ZX148848AA JESD78A, I-TEST 25C 100mA		6	0	
LATCH-UP I	1108 DS3640	ZX148848AA JESD78A, I-TEST 25C 250mA		6	0	
LATCH-UP V	1108 DS3640	ZX148848AA JESD78A, V-SUPPLY TEST 25C		6	0	
Total:						0

OPERATING LIFE

DESCRIPTION	DATE CODE/PRODUCT/LOT			CONDITION	READPOIN	QTY	FAILS	FA#
HIGH TEMP OP LIFE	0914	DS2780		WJ944804AB 125C, 5.5 VOLTS	1000 HRS	77	0	
HIGH TEMP OP LIFE	0916	DS2784		WJ943240IC- 125C, 5.5 V (PSA) & 15.0 V (PSB)	1000 HRS	77	0	
HIGH TEMP OP LIFE	0916	DS2784		WJ945481A 125C, 5.5 V (PSA) & 15.0 V (PSB)	1000 HRS	77	0	
HIGH TEMP OP LIFE	0922	DS36A92		WJ946542AB 125C, 3.6 VOLTS	192 HRS	45	0	
HIGH TEMP OP LIFE	0932	MAX17043		WJ946441P 125C, 4.5V (PSA) & 9.2V (PSB)	192 HRS	45	0	
HIGH TEMP OP LIFE	0933	DS1873		QJ917612BC 125C, 4.2 VOLTS	192 HRS	77	0	
HIGH TEMP OP LIFE	0937	DS2784		WJ046898JC 125C, 5.5 V (PSA) & 15.0 V (PSB)	1000 HRS	77	0	
HIGH TEMP OP LIFE	0940	DS2784		WJ048759A 125C, 5.5 V (PSA) & 15.0 V (PSB)	1000 HRS	80	0	
HIGH TEMP OP LIFE	0946	DS1876		WJ048840AA 125C, 4.2 VOLTS	192 HRS	77	0	
HIGH TEMP OP LIFE	0948	DS1091L		WJ946344EA 150C, 3.6 VOLTS	408 HRS	45	0	
HIGH TEMP OP LIFE	0948	DS1091L		WJ946344EA 150C, 3.6 VOLTS	408 HRS	45	0	
HIGH TEMP OP LIFE	0951	DS2784		WJ049559AB 125C, 5.5 V (PSA) & 15.0 V (PSB)	1000 HRS	80	0	
HIGH TEMP OP LIFE	0951	DS1877		WJ048842AA 125C, 4.2 VOLTS	192 HRS	77	0	
HIGH TEMP OP LIFE	1004	DS3644		WS046549D 125C, 3.6V (PSA) & 3.3V (PSB)	192 HRS	45	0	
HIGH TEMP OP LIFE	1012	MAX36051		WS048836A 125C, 3.6 VOLTS	192 HRS	45	0	
HIGH TEMP OP LIFE	1013	DS2784		WJ050375AB 125C, 5.5 V (PSA) & 15.0 V (PSB)	1000 HRS	80	0	
HIGH TEMP OP LIFE	1023	DS2784		WJ051728AB 125C, 5.5 V (PSA) & 15.0 V (PSB)	1000 HRS	80	0	
HIGH TEMP OP LIFE	1026	DS3231M		QJ048856AB 125C, 5.5 VOLTS	1000 HRS	45	0	
HIGH TEMP OP LIFE	1026	DS3231M		QJ048856AB 125C, 5.5 VOLTS	1000 HRS	45	0	
HIGH TEMP OP LIFE	1026	DS3231M		QJ048856AB 125C, 5.5 VOLTS	1000 HRS	45	0	
HIGH TEMP OP LIFE	1033	DS2784		FJ050283AB 125C, 5.5V (PSA) & 5.5V (PSB)	1000 HRS	77	0	
HIGH TEMP OP LIFE	1034	MAX17040		WS049701A 125C, 5.5V (PSA) & 5.5V (PSB)	1000 HRS	48	0	
HIGH TEMP OP LIFE	1035	DS1878		WJ055999BA 125C, 5.5 VOLTS	192 HRS	77	0	
HIGH TEMP OP LIFE	1041	DS3660		ZS156014AB 125C, 3.6V (PSA) & 3.3V (PSB)	213 HRS	48	0	
HIGH TEMP OP LIFE	1041	DS2784		ZJ160290AB 125C, 5.5V (PSA) & 5.5V (PSB)	192 HRS	80	0	

HIGH TEMP OP LIFE	1041	DS2784	ZJ160290AB	125C, 4.6 V (PSA) & 4.6 V (PSB)	1000	HRS	80	0
HIGH TEMP OP LIFE	1048	DS2784	ZJ162667AB-	125C, 4.6 V (PSA) & 4.6 V (PSB)	1000	HRS	80	0
HIGH TEMP OP LIFE	1108	DS3640	ZX148848AA	125C, 3.6V (PSA) & 3.9V (PSB)	192	HRS	45	0
						Total:		0
FAILURE RATE:			MTTF (YRS):	163796	FITS:	0.7		
			DEVICE HOURS:	1314743138	FAILS:	0		